

TECHNICAL DATA SHEET

DAN6600 Double Sided Tape

PRODUCT:

DESCRIPTION:

APPLICATIONS:

DAN6600 Double Sided Tape

White PVC double sided tape

- Permanent bonding to most substrates including metal, wood, glass, cement and plastics
- Fixing to decorative trim such as PVC profiles in the furniture industry
- Fastening name plates, luggage tags and labels
- Provides a self-adhesive finish to metal and plastic trim

Over 72 hours, 1kg loading on 25mm x 25mm at 25°C

Over 24 hours, 1kg loading on 25mm x 25mm at 70°C

Permanent carpet laying

Acrylic on both sides

0.21mm

8 kg/mm²

180%

2.4 kg/25mm

90gsm amber glassine release liner

0.05mm unplasticized PVC film

TECHNICAL SPECIFICATIONS:

Release Liner

Carrier Material

Adhesive Type

Total Thickness

Peel Adhesion (PSTC-3)

Shear Strength (PSTC-7)

Heat Resistance

Tensile Strength (machine direction)

Elongation (machine direction)

Service Temperature

Colour Available Sizes Available

-20°C to +90°C (short term) White

12mm x 50m = 36 Rolls / Carton

18mm x 25m = 48 Rolls / Carton

10111111 X 23111 = 46 holls / Gartor

 $24mm \times 25m = 40 \text{ Rolls / Carton}$ $24mm \times 50m = 36 \text{ Rolls / Carton}$

36mm x 25m = 24 Rolls / Carton

48mm x 25m = 20 Rolls / Carton

 $48mm \times 50m = 20 \text{ Rolls / Carton}$

100mm x 50m = 8 Rolls / Carton 300mm x 25m = 4 Rolls / Carton

1000mm x 50m = 1 Roll / Carton

STORAGE: Rolls and cartons of tape should be stored in a cool area

and out of direct sunlight

PRODUCT PROPERTIES:

- · High tack that provides quick bonding
- High peel adhesion
- · Good resistance against solvents, chemicals, UV and heat

OCTOBER 2024

It is the customer's responsibility to ensure that a particular product with the properties described in this product specification is suitable for use in a specific situation. No warranty, representation or guarantee is given by us regarding the suitability of this product for any particular use. The physical and performance characteristics shown are averages obtained from tests as per PSTC, ASTM and our own internal procedures. A particular roll may vary from these averages. It is suggest that the customer determine the suitability for their own purpose by conducting a rigorous trial process.

